

IN THE CLAIMS

Please amend the claims as follows:

Claims 1-7 (Canceled).

Claim 8 (Currently Amended): A waterproof and breathable sole for shoes,
comprising:

a mid-sole component ~~comprising~~ including:

a membrane made of a material that is impermeable to water and permeable to
water vapor;

a lower protective layer made of a material that is resistant to hydrolysis,
water-repellent, breathable, and/or perforated; ~~said, the~~ membrane being connected in
spots with said lower protective layer; and

a tread made of perforated elastomer that is joined perimetrically and hermetically to
the component; ~~and,~~

wherein said membrane is associated with said protective layer by a thermoreactive
adhesive.

Claim 9 (Previously Presented): The sole of claim 8, wherein said membrane and
said protective layer associated therewith are joined hermetically to said tread, which is
provided by overmolding or in place assembling on said component.

Claim 10 (Previously Presented): The sole of claim 8, wherein said membrane and
said protective layer are part of a mid-sole with a preassembled insert that comprises a
perimetric element that is overmolded or assembled in place and surrounds said membrane

and said protective layer and is joined to them hermetically, said insert being coupled to said tread, which is overmolded or assembled in place thereon.

Claim 11 (Canceled).

Claim 12 (Currently Amended): A method for joining a membrane made of a material that is impermeable to water and permeable to water vapor to a protective layer made of a material that is resistant to hydrolysis, water-repellent, breathable and/or perforated, to provide waterproof and breathable soles for shoes, the method comprising:

applying ~~in spots~~ thermoreactive adhesives in spots between said membrane and said protective layer.

Claim 13 (Canceled).

Claim 14 (Previously Presented): A method for making a waterproof and breathable sole for shoes that has a structure including a mid-sole component with a membrane made of a material that is impermeable to water and permeable to water vapor and is connected in spots with a lower protective layer made of a material that is resistant to hydrolysis, water-repellent, breathable and/or perforated; and a tread made of perforated elastomer that is joined perimetrically and hermetically to the component[[;]], the method comprising:

connecting said membrane to said protective layer [[by]] with a thermoreactive adhesive.